

### CHEMICAL RESISTANT CHART

Rating Key: 0 - No Effect    1 - Not Recommended    2 - Etch & Softens Surface

| <u>Chemical</u>                    | <u>Immersion</u> | <u>Splash or Spill</u> |
|------------------------------------|------------------|------------------------|
| 5% Hydrochloric Acid.....          | 1                | 0                      |
| 10% Hydrochloric Acid.....         | 1                | 0                      |
| 20% Hydrochloric Acid.....         | 1                | 0                      |
| 37% Hydrochloric Acid.....         | 1                | 0                      |
| 5% Sulfuric Acid.....              | 0                | 0                      |
| 10% Sulfuric Acid.....             | 1                | 0                      |
| 25% Sulfuric Acid.....             | 1                | 0                      |
| 50% Sulfuric Acid.....             | 1                | 1                      |
| 5% Nitric Acid .....               | 1                | 0                      |
| 10% Nitric Acid .....              | 1                | 0                      |
| 5% Acetic Acid.....                | 1                | 0                      |
| 20% Acetic Acid.....               | 1                | 0                      |
| 100% Acetic Acid.....              | 1                | 1                      |
| 100% Fatty Acids.....              | 1                | 0                      |
| 10% Ammonium Hydroxide .....       | 0                | 0                      |
| 50% Sodium Hydroxide.....          | 0                | 0                      |
| 20% Sodium Chloride in Water.....  | 0                | 0                      |
| 20% Calcium Chloride in Water..... | 0                | 0                      |
| 12% Sodium Hypochlorite .....      | 1                | 2                      |
| Motor Oil.....                     | 0                | 0                      |
| Mineral Spirits.....               | 0                | 0                      |
| Gasoline .....                     | 0                | 0                      |
| Xylene.....                        | 1                | 0                      |
| Toluene .....                      | 1                | 0                      |
| Hydraulic Fluid.....               | 0                | 0                      |
| Carbon Tetrachloride .....         | 0                | 0                      |
| Trichloroethane.....               | 1                | 0                      |
| Methyl Alcohol .....               | 1                | 0                      |
| Ethyl Alcohol.....                 | 1                | 0                      |
| Ethylene Glycol (Antifreeze).....  | 0                | 0                      |
| Glycerine .....                    | 0                | 0                      |
| Methyl Ethyl Ketone.....           | 1                | 0                      |
| Methylisobutyl Ketone .....        | 1                | 0                      |
| Cellosolve Acetate.....            | 1                | 0                      |

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 10052006/7430SeriesCRC.indd

