

### CHEMICAL RESISTANT CHART

Rating Key: 0 - No Effect    1 - Stains/Dulls    2 - Blisters    3 - Lifts Film

<u>Chemical</u>	<u>Rating</u>
Ammonia 28% .....	0
Bleach .....	1
Brake Fluid .....	2
Calcium Chloride 10%.....	0
Ethylene Glycol .....	0
Hydrochloric Acid 5% .....	0
Hydrochloric Acid 15% .....	0
Isopropyl Alcohol .....	0
Jet Fuel .....	0
Gasoline .....	0
Mineral Spirits .....	0
Motor Oil.....	0
Nitric Acid 5% .....	1
Oleic Acid .....	0
Phosphoric Acid 10% .....	1
Propylene Glycol .....	0
Sodium Hypochlorite 10%.....	0
Sodium Hydroxide 20%.....	0
Sodium Hydroxide 50%.....	0
Soya Oil.....	0
Sulfuric Acid 5% .....	0
Sulfuric Acid 10% .....	0
Sulfuric Acid 20% .....	0
Tall Oil Fatty Acid.....	0

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of NEOGARD®, a division of JONES-BLAIR® Company. 09102006/FC7520CRC.indd

